

Density of parts	1.04 g/cm ³
Tensile strength, max load, XYZ	50 MPa/7250 psi
Tensile modulus, XYZ	1800 MPa/261 ksi
Tensile modulus, Z	1800 MPa/261 ksi
Elongation at break, XYZ	50%
Flexural strength (@ 5%), XYZ	60 MPa/8700 psi
Flexural modulus, XYZ	1600 MPa/232 ksi
Izod impact notched (@ 3.2 mm, 23°C), XYZ	6 kJ/m ²
Heat deflection temperature (@ 0.45 MPa, 66 psi), Z	183°C/361°F
Heat deflection temperature (@ 1.82 MPa, 264 psi), XY	50°C/122°F