

Tensile strength at break	60 ± 1.0 MPa
Young's modulus	1890 ± 52 MPa
Elongation at failure	47 ± 8%
Flexural stress at yield	80.6 ± 1.3 MPa
Flexural modulus	1,856 ± 130 MPa
Flexural strain at break	>10%
IZOD impact strength (notched)	53.8 ± 3 J/m
HDT @ 0.455 MPa (VICAT)	56 °C
Water Absorption	2.35%