

Elongation at break .....	26-46%
Tensile strength .....	18-28 MPa
Tensile modulus .....	520-840 MPa
Notched IZOD impact .....	31-37 J/m
Volume shrinkage .....	7.5%
Linear shrinkage .....	2.6%
Shore D hardness .....	60