

E modulus .....	1990 MPa
Tensile strength .....	49 MPa
Elongation at break .....	3%
Flexural modulus .....	2330 MPa
Flexural strength @ 5% strain .....	108 MPa
Notched Izod 23°C .....	18 J/m
HDT @ 0.45 MPa .....	61°C
HDT @ 1.82 MPa .....	51°C
Shore D hardness .....	80
Viscosity @ 23°C .....	1090 mPas
Viscosity @ 30°C .....	613 mPas
Viscosity @ 50°C .....	164 mPas